


Base Resin	Polyether Block Amide (PEBA)
Compound Type	 Compound 1002 Series - Medium and High Density
Processing Method	Extrusion

Process Guidelines

Processing Conditions	Material Drying
<ul style="list-style-type: none"> • Process Temperature Range.. 325 - 365 °F • Die Temperature Range..... 330 - 345 °F • Chill Roll Temp. Range..... 110 - 125 °F 	<ul style="list-style-type: none"> • Dryer Type(s)..... Dehumidifying • Drying Temperature Range... 140 °F • Typical Drying Time¹..... 4 - 8 hrs • Do Not Exceed..... 160 °F • Dryer Dew Point..... -20 to -40°F • Minimum Air Flow..... 0.8 - 1.0 CFM • Properly Functioning..... Desiccant Beds Filters Volatiles Trap

Machine Requirements	Safety / Purging
<ul style="list-style-type: none"> • No special requirements 	<ul style="list-style-type: none"> • Maintain adequate ventilation. • Wear safety glasses & protective clothing. • Do not mix with other materials. • Avoid excessive residence time in the barrel. (Purge if extended residence time is anticipated) • Use extreme caution at melt temp. > 600°F
	Purge with high viscosity HDPE or high temperature commercial purge compound as recommended.

Notes

¹ Typical Drying time assumes unopened packaging and utilization of a dehumidifying dryer with a dew point of -40° with sufficient air flow.

² Pack time can depend on wall thickness and gate design

The processor of these materials is advised and cautioned to make an independent determination and assessment of the safety and suitability of the material for the specific use in question and is further advised against relying on the information herein as it may relate to any specific use or application. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.