



The strength of chemicals.

4917 Golden Parkway - Suite 300  
Buford, GA 30518  
770-237-2311



# Technical Data Sheet

Preliminary

**Material:** Ecomass® Compound 5100TU96

*Nontoxic alternative to Lead (Pb), weighting, balancing and radiation shielding applications*

**Description / Features:** High Specific Gravity, Tungsten Powder Filled SEBS Base Resin, Very Flexible

**Processing Method:** Injection Molding

## Physical Properties

	Test Method	Value	Units
<b>Physical Properties</b>			
Product Form		Pellets	
Specific Gravity	ASTM D792	11.00	
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D638	196	psi
Tensile Modulus	ASTM D638	N/A	psi
Tensile Elongation at Break	ASTM D638	177	%
Flexural Modulus	ASTM D790	13,300	psi
Flexural Strength	ASTM D790	386	psi
Izod Impact Strength, notched	ASTM D256	2.0	ft-lb/in
Hardness	ASTM D2240	23	Shore D
<b>Thermal Properties</b>			
Heat Deflection Temperature	ASTM D648	N/A	°F
Heat Deflection Temperature	ASTM D648	N/A	°F
<b>Electrical Properties</b>			
Surface Resistivity	ASTM D257	N/A	ohms/sq
<b>Processing Information</b>			
Melt Temperature Range		300 - 400	°F
Mold Temperature Range		70 - 100	°F
Mold Shrinkage Rate	ASTM D955	0.003 - 0.005	in/in
Pre-Drying Conditions		Not Required	

The information provided above is based on laboratory testing using test methods indicated and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.

Ecomass® Compounds are manufactured by DOMO Engineering Plastics US under license from Ecomass Technologies

Ecomass® is a registered trademark