



**The strength of chemicals.**  
 4917 Golden Parkway - Suite 300  
 Buford, GA 30518  
 770-237-2311

# Technical Data Sheet



**Material:** Ecomass® Compound 4703BI71

*Nontoxic alternative for shielding, weighting, balancing, and vibration dampening applications*

**Description / Features:** Moderate Specific Gravity, Filled Polyurethane (TPU), Good Flexibility

**Processing Method:** Injection Molding

## Physical Properties

	Test Method	Value	Units
<b>Physical Properties</b>			
Product Form		Pellets	
Specific Gravity	ASTM D792	2.50	
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D638	2,900	psi
Tensile Modulus	ASTM D638	80,000	psi
Tensile Elongation at Break	ASTM D638	220	%
Flexural Modulus	ASTM D790	24,500	psi
Flexural Strength	ASTM D790	6,400	psi
Izod Impact Strength	ASTM D256	4.60	ft-lb/in
<b>Thermal Properties</b>			
Heat Deflection Temperature at 66 psi	ASTM D648	N/A	°F
Heat Deflection Temperature at 264 psi	ASTM D648	N/A	°F
<b>Electrical Properties</b>			
Surface Resistivity	ASTM D257	N/A	ohms/sq
<b>Processing Information</b>			
Melt Temperature Range		400 - 430	°F
Mold Temperature Range		50 -80	°F
Mold Shrinkage Rate	ASTM D955	0.006 - 0.008	in/in
Pre-Drying Conditions		2hrs @ 180 °F (do not over-dry)	

The information provided above is based on laboratory testing using test methods indicated and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.