



The strength of chemicals.
 4917 Golden Parkway - Suite 300
 Buford, GA 30518
 770-237-2311

Technical Data Sheet



Material: Ecomass® Compound 4703BI74
Nontoxic alternative to Lead (Pb), radiation shielding applications

Description / Features: Moderate Specific Gravity, Filled Polyurethane (TPU), Good Flexibility

Processing Method: Injection Molding

Physical Properties

	Test Method	Value	Units
Physical Properties			
Product Form		Pellets	
Specific Gravity	ASTM D792	2.60	
Mechanical Properties			
Tensile Strength	ASTM D638	2,800	psi
Tensile Modulus	ASTM D638	80,000	psi
Tensile Elongation at Break	ASTM D638	200	%
Flexural Modulus	ASTM D790	25,000	psi
Flexural Strength	ASTM D790	6,400	psi
Izod Impact Strength	ASTM D256	4.50	ft-lb/in
Thermal Properties			
Heat Deflection Temperature at 66 psi	ASTM D648	N/A	°F
Heat Deflection Temperature at 264 psi	ASTM D648	N/A	°F
Electrical Properties			
Surface Resistivity	ASTM D257	N/A	ohms/sq
Processing Information			
Melt Temperature Range		400 - 430	°F
Mold Temperature Range		50 - 80	°F
Mold Shrinkage Rate	ASTM D955	0.006 - 0.008	in/in
Pre-Drying Conditions		2hrs @ 180 °F (do not over-dry)	

The information provided above is based on laboratory testing using test methods indicated and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.