Americhem Engineered Compounds Safety Data Sheet Ecomass Compounds 0700BI Series

According to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

SECTIO	N 1: Identification							
1(a)	Product Identifier used on label							
	Ecomass Compounds:	070	OBI Series	5				
	Form:	Plas	tic Compo	ound (Ad	rylonitrile-E	Butadiene-Styre	ne) & Metall	ic Powder Mixture
		(Pel	lets)					
1(b)	Other means of identification							
	ABS							
1(c) Recommended use of the chemical and restrictions on use								
1. Uses: Thermoplastic Polymer for Injection Molding and Extrusion								
	2. Restrictions on Uses: None							
1(d)	Name, address, & telephone number of the chemical manufacturer, importer, or supplier							
	Americhem Engineered Compou	inds						
	20 Progress Drive							
	Morrisville, PA 19067 USA							
	215-736-1126							
1(e)	Emergency phone number							
	215-736-1126							

SECTIO	N 2: Hazard(s) Identification	
2(a)	Hazard Classification	
	(GHS-US):	Not classified as a hazardous substance or mixture.
2(b)	Label Elements	
	Signal Word:	None
	Pictogram:	None
	Hazard Statements:	None
	Supplemental Hazard Statement:	Processing may release vapors and/or fumes which cause eye, skin, and respiratory tract irritation. Severe over-exposure may result in nausea, headache, chills, and fever. See below for additional effects. Secondary operations, such as grinding, sanding, or sawing can produce dust which may present an explosion or respiratory hazard.

2(c) Hazards not otherwise classified

This material has not been evaluated as a whole. All ingredients are bound in a polymer matrix and potential for hazardous exposure as shipped is minimal. However, some fumes may be released upon heating and the end-user (fabricator) must take the necessary precautions (mechanical ventilation, respirator program, etc.) to protect his employees from exposure which may cause eye, skin, and respiratory tract irritation. Prolonged or repeated exposure may cause: headache, drowsiness, nausea, weakness (severity of effects depends on extent of exposure). (See Section 8 - Exposure Controls / Personal Protection) The following ingredients are considered hazardous per OSHA 1910.1200:

- 1. Metallic Powder
- 2. Nuisance Dust

2(d) Ingredients with unknown toxicity

None

SECTION 3: Composition / Information on Ingredients

Products as manufactured are classified as non-hazardous and chemical disclosure is not required by regulation(s).

While not required, polymers and metal powders are described below with their CAS Number(s).

If a chemical is not specifically identified, it is considered proprietary.

Each barium sulfate powder particle is bound in a polymer matrix mixture and potential for hazardous exposure as shipped is minimal.

The specific chemical identity and/or exact percentage (concentration) of composition has been withheld as a trade secret.

Name	Product I dentifier	%	Classification (GHS-US)
(ABS) Acrylonitrile-Butadiene-Styrene	(CAS No) 9003-56-9	< 100	Not classified
Barium Sulfate	(CAS No) 7727-43-7	< 100	Hazardous based on components

SECTION 4: First Aid Measures

4(a) Description of First Aid Measures

	After Inhalation:	No known effects during normal usage. If inhalation of processing vapors from overheating or combustion, supply fresh air. In cases of severe exposure, nausea and headache can also occur. Consult physician.	
immediately flush with cool wat medical treatment. After Eye Contact: No known effects. Rinse eyes w immediately flush with cool wat		No known effects. Wash contacted skin. If contact with molten product, immediately flush with cool water. DO NOT pull solidified product off skin. Seek medical treatment.	
		No known effects. Rinse eyes with water. If contact with molten product, immediately flush with cool water. Seek medical treatment.	
		No known effects. DO NOT induce vomiting. Seek medical treatment.	
4(b)	Most important symptoms and effects, both acute and delayed		
	Symptoms/Injuries:	No known effects. Long term skin contact could cause skin dryness.	
4(c)	Indication of any immediate medical attention and special treatment needed		
	Treat symptoms as above. No specific antidote. Consult physician and/or seek medical treatment.		

SECTION 5: Fire Fighting Measures

5(a)	Suitable Extinguishing Media			
	Water spray, dry chemical, carbon dioxide (CO ₂), or "Alcohol" foam. For large fires use water spray for its cooling capacity			
	to reduce chances of reignition, and call for fire-fighting assistance.			
	Unsuitable Extinguishing Media			
	Do not use a solid water stream, as it may scatter and spread fire.			
5(b)	Specific hazards arising from the substance or mixture			
	Fire hazard:	Flash point : >660 °F (>349 °C). Not flammable under ordinary use conditions but will burn and produce dense black smoke. The following hazardous products of combustion can occur: hydrogen cyanide (hydrocyanic acid) (traces), hydrocarbon fragments, and trace amounts of oxides of carbon and nitrogen.		
	Explosion hazard:	Static charge buildup can be a potential fire hazard when used in the presence of volatile, flammable vapors or in high airborne dust concentrations.		
	Reactivity:	Non-reactive.		
5(c)	Advice for Fire Fighters			
	Precautions:	Use standard protective clothing for fire fighters. Self contained breathing apparatus should be worn to prevent inhalation of smoke and decomposition products in the event the material should burn. Decontaminate fire fighting equipment after use.		

SECTION	SECTION 6: Accidental Release Measures			
6(a)	Personal precautions, protective e	quipment and emergency procedures		
	General measures:	If spilled, may cause a fall or slipping hazard. Avoid dust generation. Keep away		
		from ignition sources. Ensure proper ventilation.		
Environmental: Avoid dispersal d		Avoid dispersal of spilled material and runoff and contact with soil, waterways, drains		
	Environmental.	and sewers. Prevent entry to sewers and public waters.		
6(b)	Methods and material for containment and cleaning up			
	Containment:	Prevent further leakage or spillage if you can do so without risk. Ventilate the area.		
		Shovel, scoop, sweep up or use industrial vacuum cleaner and return to original		
		container. Products are non-hazardous waste. Proper disposal should be evaluated		
		based on local, state, and federal regulations/legislation or directives. Users must		
		determine if a report is required to EPA for any amounts of this material disposed of		
		or otherwise released into the environment.		
	References:	Refer to Sections 7, 8, and 13.		

SECTION 7: Handling and Storage

7(a) Precautions for Safe Handling

Prevent generation of dust and avoid breathing dust. If necessary, wear a dust mask. Avoid breathing processing fumes or vapors and use local exhaust above processing areas. Wash hands after use. Avoid eating, drinking, and smoking in work areas. Handle in accordance with good industrial hygiene and safety practices. These practices include avoiding unnecessary exposure and removal of material from eyes, skin, and clothing. Take precautionary measures against static discharge. Earth/Ground processing equipment. Product may accumulate static charge during transport, handling, and processing. Considering the risks of electrostatic discharges, handling the products in potentially flammable atmospheres should be evaluated. Suitable precautions should be taken at all times, in particular when emptying bags or other packaging. Reducing the velocity of transport will reduce charging. Static charge buildup can be a potential fire hazard when used in the presence of volatile or flammable mixtures. Keep away from ignition sources. If product is processed into smaller particles, explosive hazardous conditions must be evaluated. The temperatures listed are indicated only for safety reasons (risk of fire and product degradation) and are not recommended for processing. Degradation of the polymer may start at lower temperatures depending on the specific processing conditions.

7(b) Conditions for safe storage, including any incompatibilities

Stable under recommended storage conditions. Do not store outside. Keep container dry. Keep in a cool, dry, wellventilated place. Store in closed containers, in a secure area to prevent container damage and subsequent spillage. Store away from moisture and heat to maintain the technical properties of the product. Avoid storage under pressure or at elevated temperatures above to minimize particulate clustering. Do not store above 140 °F (60 °C). Do not store with alkalis, oxidizers or acids.

7(c) Specific end use(s)

No additional information available.

SECTION 8: Exposure Controls / Personal Protection			
8(a)	Exposure Control Limits - ABS (Acrylonitrile-Butadiene-Styrene)		
		Form	TWA (Time Weighted Average)
	ACGIH	Inhalable Particles	10 mg/m ³
		Respirable Particles	3 mg/m ³

OSHA Table Z-1	Form	PEL (Permissable Exposure Limit)
Limits for Air	Respirable Fraction	5 mg/m ³
Contaminants	Total Dust	15 mg/m ³

	Form	TWA (Time Weighted Average)
	Respirable Fraction	15 ppm
OSHA Table Z-3	Total Dust	50 ppm
	Respirable Fraction	5 mg/m ³
	Total Dust	15 mg/m ³

Exposure Control Limits - Barium Sulfate

ACGIH	Form	TWA (Time Weighted Average)
Acom	as Barium Sulfate	10 mg/m ³

OSHA Table Z-1	Form	PEL (Permissible Exposure Limit)
Air Contaminants	Respirable Fraction	5 mg/m ³
	Total Dust	15 mg/m ³

	Form	IDLH (Immediately Dangerous to Life or Health)
NIOSH IDLH	Respirable Fraction	5 mg/m ³
	Total Dust	15 mg/m ³

8(b) Appropriate Engineering Controls

Use local exhaust ventilation during processing to reduce exposures below above limits. Processing fume condensate may be a fire hazard and toxic; remove periodically from exhaust hoods, ductwork, and other surfaces using appropriate personal protection. When transferring products, earth/ground all subsequent equipment to minimize charges that may develop.

8(c) **Individual Protection Measures**

Eye protection:

Personal protective equipment:

Safety Glasses. Protective Clothing. Gloves.



Materials for protective clothing: Standard issue work clothes, which may include apron, antistatic safety shoes or boots as necessary. Use good industrial practice to avoid eye contact. Wear safety glasses with sideshields. Processing of this product releases vapors or fumes which may cause eye irritation. Where eye contact may be likely, wear chemical goggles and have eye flushing equipment available. Use full-face shield when cleaning processing vapor condensates from hood, ducts, and other surfaces. Processing of this product releases vapors or fumes which may cause skin irritation.

Skin: Minimize skin contamination by following good industrial hygiene practice. Wearing protective gloves is recommended. Use heat protective gloves when handling hot, molten product. Grease-like processing vapor condensates on ventilation ductwork, molds, and other surfaces can cause irritation and injury to skin. Wash hands and contaminated skin thoroughly after contact with processing fumes or vapors or after

Avoid breathing dust. Avoid breathing processing fumes or vapors. During handling: if dust is generated, a parliculate pre-filter is recommended and for high airborne dust concentrations, a cartridge designed for nuisance dust is recommended. During high temperature processing: use local exhaust ventilation when available. Consult respirator manufacturer to determine appropriate type equipment for a given application. Observe respirator use limitations specified by NIOSH or the manufacturer. For emergency and other conditions where there may be a potential for significant exposure or where exposure limit may be significantly exceeded, use an approved full face positive-pressure, self-contained breathing apparatus or positivepressure airline with auxiliary self-contained air supply. Respiratory protection programs must comply with 29 CFR § 1910.134.

Appearance/Form:Pellets; porous to denseColor:Various: tan, copper, gray or black - dependent on filler material9(b)Odor:Essentially odorless, may be faint odor9(c)Odor threshold:Not determined9(d)pH:No data available9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide range of temperatures.Softening point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable9(j)Ipper / Lower Flammability:Not data available9(j)Upper / Lower Flammability:Not data available9(j)Qipsive Limits:Not Applicable, Solid9(j)Qipsive Limits:Not Applicable, Solid9(j)Vapor pressure:Not Applicable, Solid9(j)Vapor pressure:Not Applicable, Solid9(j)Vapor pressure:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insoluble9(n)Partition Coefficient:No data available9(n)Partition Coefficient: <th>SECTIO</th> <th>N 9: Physical and Chemical Properties</th> <th>5</th>	SECTIO	N 9: Physical and Chemical Properties	5
Color:Various: tan, copper, gray or black - dependent on filler material9(b)Odor:Essentially odorless, may be faint odor9(c)Odor threshold:Not determined9(d)pH:No data available9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide range of temperatures.Softening point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Ipper / Lower Flammability:Not data available9(k)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insoluble9(n)Solubility (water):68 °F (20 °C) insoluble9(n)Solubility (water):68 °F (20 °C) insoluble9(n)Solubility (other):No data available9(n)Partition Coefficient:No data available9(n)Solubility (other):No data available9(n)Solubility (other):572 °F (>400 °C)9(n)Partition Coefficient:No data available9(n)Partition Coefficient:No data available9(n)Partition Coefficient:No data available9(n)Solubility (other):572 °F (>400 °C)9(n)Partition Coefficie	9(a)	Physical state:	Solid
9(b)Odor:Essentially odorless, may be faint odor9(c)Odor threshold:Not determined9(d)pH:No data available9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide range of temperatures.9(e)Melting point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(g)Flash point:Not Applicable9(g)Flash point:Not Applicable9(g)Flash point:Not Applicable, Solid9(i)Evaporation rate:Not data available9(j)Ipper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not data available9(j)Vapor pressure:Not Applicable, Solid9(l)Vapor pensity:Not Applicable, Solid9(l)Vapor pensity:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (water):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable, Solid °C)		Appearance/Form:	Pellets; porous to dense
9(c)Odor threshold:Not determined9(d)pH:No data available9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide range of temperatures.9(e)Melting point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>572 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable		Color:	Various: tan, copper, gray or black - dependent on filler material
9(d)PH:No data available9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide rage of temperatures.9(e)Softening point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:Not Applicable9(g)Flash point:Not Applicable, Solid9(h)Evaporation rate:Not Applicable, Solid9(h)Evaporation rate:Not dat available9(h)Upper / Lower Flammability:Not dat available9(h)Upper / Lower Flammability:Not dat available9(h)Vapor pressure:Not Applicable, Solid9(h)Vapor pressure:Not Applicable, Solid9(h)Relative density:Specific Gravity: 1 - 39(h)Solubility (water):Sole °C °C) insoluble9(h)Partition Coefficient:No data available9(h)Partition Coefficient:No data available9(h)Auto-Ignition Temperature:>752 °F (>400 °C)9(h)Decomposition temperature:>572 °F (>300 °C)9(h)Viscosity, Kinematic:Not Applicable	9(b)	Odor:	Essentially odorless, may be faint odor
9(e)Melting point:This product does not exhibit a sharp melting point but softens gradually over a wide range of temperatures.9(a)Softening point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:60° °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):Not Applicable, Solid9(j)Upper / Lower Flammability:Not dat available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(k)Vapor pressure:Not Applicable, Solid9(k)Vapor pressure:Not Applicable, Solid9(k)Relative density:Specific Gravity: 1 - 39(n)Relative density:Specific Gravity: 1 - 39(n)Solubility (other):No dat available9(n)Partition Coefficient:No dat available9(n)Auto-Ignition Temperature:>752 °F (>400 °C)9(n)Decomposition temperature:>572 °F (>300 °C)9(n)Nicosity, Kinematic:Not Applicable	9(c)	Odor threshold:	Not determined
inage of temperatures.Softening point:50-180 °F (66-82 °C)Freezing point:Not Applicable9(m)Boiling point:Not Applicable9(m)Flash point:60°F (349 °C)9(m)Evaporation rate:Not Applicable, Solid9(m)Flamability (solid, gas):Not Applicable9(m)Upper / Lower Flamability:Not Adatavailable9(m)Upper / Lower Flamability:Not Adatavailable9(m)Vapor persure:Not Applicable, Solid9(m)Vapor persure:Not Applicable, Solid9(m)Relative density:Socific Gravity: 1-39(m)Solubility (water):Socific Gravity: 1-39(m)Solubility (water):Not Apavailable9(m)Partition Coefficient:Not Available9(m)Partition Coefficient:Not Available9(m)Partition Temperature:>752 °F (>400 °C)9(m)Notosyt, Kinematic:Not Applicable, Solid °C)9(m)Notosyt, Kinematic:Not Applicable	9(d)	pH:	No data available
Softening point:150-180 °F (66-82 °C)Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(n)Relative density:Specific Gravity: 1 - 39(n)Solubility (other):SolubileSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinemati:Not Applicable	9(e)	Melting point:	This product does not exhibit a sharp melting point but softens gradually over a wide
Freezing point:Not Applicable9(f)Boiling point:Not Applicable9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):Not dat available9(i)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable			range of temperatures.
9(f)Boiling point:Not Applicable9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(n)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable		Softening point:	150-180 °F (66-82 °C)
9(g)Flash point:660 °F (349 °C)9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:No data available9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(n)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable		Freezing point:	Not Applicable
9(h)Evaporation rate:Not Applicable, Solid9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data availableExplosive Limits:Not determined9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(f)	Boiling point:	Not Applicable
9(i)Flammability (solid, gas):No data available9(j)Upper / Lower Flammability:No data available9(j)Upper / Lower Flammability:Not determined9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(g)	Flash point:	660 °F (349 °C)
9(j)Upper / Lower Flammability:No data availableExplosive Limits:Not determined9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(h)	Evaporation rate:	Not Applicable, Solid
Explosive Limits:Not determined9(k)Vapor pressure:Not Applicable, Solid9(n)Vapor Density:Not Applicable, Solid9(n)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insoluble9(n)Solubility (other):No data available9(n)Partition Coefficient:No data available9(n)Auto-Ignition Temperature:>752 °F (>400 °C)9(n)Decomposition temperature:>572 °F (>300 °C)9(n)Viscosity, Kinematic:Not Applicable	9(i)	Flammability (solid, gas):	No data available
9(k)Vapor pressure:Not Applicable, Solid9(l)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(n)Partition Coefficient:No data available9(n)Auto-Ignition Temperature:>752 °F (>400 °C)9(n)Decomposition temperature:>572 °F (>300 °C)9(n)Viscosity, Kinematic:Not Applicable	9(j)	Upper / Lower Flammability:	No data available
9(I)Vapor Density:Not Applicable, Solid9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable		Explosive Limits:	Not determined
9(m)Relative density:Specific Gravity: 1 - 39(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(k)	Vapor pressure:	Not Applicable, Solid
9(n)Solubility (water):68 °F (20 °C) insolubleSolubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(I)	Vapor Density:	Not Applicable, Solid
Solubility (other):No data available9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(m)	Relative density:	Specific Gravity: 1 - 3
9(o)Partition Coefficient:No data available9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(n)	Solubility (water):	68 °F (20 °C) insoluble
9(p)Auto-Ignition Temperature:>752 °F (>400 °C)9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable		Solubility (other):	No data available
9(q)Decomposition temperature:>572 °F (>300 °C)9(r)Viscosity, Kinematic:Not Applicable	9(o)	Partition Coefficient:	No data available
9(r) Viscosity, Kinematic: Not Applicable	9(p)	Auto-Ignition Temperature:	>752 °F (>400 °C)
	9(q)	Decomposition temperature:	>572 °F (>300 °C)
	9(r)	Viscosity, Kinematic:	Not Applicable
Viscosity, Dynamic: Not Applicable		Viscosity, Dynamic:	Not Applicable
Other Oxidizing properties: No data available	Other	Oxidizing properties:	No data available

SECTION	SECTION 10: Stability and Reactivity				
10(a)	Reactivity:	Non-reactive. The product is stable under normal handling and storage conditions.			
10(b)	Chemical Stability:	Stable under ambient conditions. Hazardous polymerization does not occur.			
10(c)	Possibility of Hazardous Reactions:	Non-reactive. The product is stable under normal handling and storage conditions.			
10(d)	Conditions to Avoid:	Avoid prolonged exposure to heat or UV light since this may affect product properties. Product will burn when exposed to continuous sources of ignition. To avoid thermal decomposition (>572 °F (>300 °C)), avoid elevated temperatures which can result in the formation of gaseous decomposition products, some of which may be hazardous. Do not allow product to remain in barrel at elevated temperatures for extended periods of time. See Hazardous Decomposition below.			
10(e) 10(f)	Incompatible Materials: Hazardous Decomposition:	Avoid contact with strong oxidizing agents. Hazardous vapors from heated product are not expected to be generated under normal processing temperatures and conditions. Process vapors under recommended processing conditions may include trace levels of hydrocarbons, styrene, acrylonitrile, acrolein, acetaldehyde, acetophenone, ethyl benzene, cumene, alpha methylstyrene, 4-vinylcyclohexene, phenols. Although highly dependent on temperature and environmental conditions, a variety of thermal decomposition products may be present if the product is overheated (>572 °F (>300 °C)), is smoldering, or catches fire. The following hazardous toxic, flammable, and/or corrosive products of combustion can occur: hydrogen cyanide (hydrocyanic acid) (traces), hydrocarbon fragments, and trace amounts of oxides of carbon (CO _x), and			

SECTIO	SECTION 11: Toxicological Information			
11(a) Routes of Exposure				
	Aspiration hazard:	(Rat) LD50 > 5,000 mg/kg (estimated).		
	Skin corrosion/irritation:	Not irritating. (Rabbit) LD50 > 2,000 mg/kg (estimated).		
	Serious eye damage/irritation:	Resin particles, like other inert materials, are mechanically irritating to eyes.		
	Respiratory:	Pellet ingestion unlikely due to physical form.		
	Ingestion:	Pellet ingestion unlikely due to physical form.		
11(b)	Symptoms	See Section 4		
11(c)	Effects - Short and Long Term			
	Germ Cell Mutagenicity:	Not classified; (No data available)		
	Carcinogenicity:	Not classified; (No data available)		
11/4	Tovicity			

11(d) Toxicity

Toxicity Overview:

This product contains the following components which in their pure form have the following characteristics:

	CAS-No.	Chemical Name	Effect	Target Organ
	CA3 110.	Chernical Name		
	7727-43-7 Barium Sulfate	Irritant	Respiratory system	
		Systemic effects	Eyes, Respiratory system	

Chronic Toxicity:

Styrene: Genotoxicity - In several in vitro bacterial mutagenicity tests using Salmonella typhimurium tester strains TA98, TA100, TA1535, and TA1537 at concentrations up to 1 mg/plate, styrene has been found to test negative without metabolic activation and has tested either equivocal or negative with metabolic activation. In standard mammalian cells tested in vitro, no mutagenicity was observed. When using in vivo test systems, styrene did not induce chromosome aberrations in mouse bone marrow cells but did increase sister chromatid exchanges (SCE) at concentration of 250 ppm and above for 14 days. Subchronic Toxicity: Styrene: Many repeat dose toxicity studies are available in several test animal species following both oral and inhalation exposure. In rats dosed orally, effects on liver (changes in enzyme levels and increased weight) were consistently observed at concentrations of 350 mg/kg and higher. Gastrointestinal irritation and kidney weight changes are observed at higher doses. Findings were similar for beagle dogs. The no observed effect levels (NOEL) ranged from 100 mg/kg/day to about 300 mg/kg/day, depending on the duration of exposure. A series of inhalation studies were conducted in the 1940s and 1950s. Rats, guinea pigs, rabbits, and monkeys were exposed up to 8 hours/day, 5 days/week for 6 months to 650 to 2000 ppm (3 – 9.3 mg/L) and consistent signs of significant eye and nose irritation were observed at 1300 ppm and above. Histopathological lesions at this concentration typically consisted of pulmonary lesions. **Special Studies:** Styrene: A reproduction study in rats exposed to 125 and 250 ppm in drinking water (approximately 14-21 mg/kg/day) produced no treatment-related effects on reproductive performance over 3- generations. The only treatment related findings were reduced pup survival index in the F1 and F2 offspring. There was no evidence of developmental effects and no other effects were reported. The parental NOEL was 250 ppm and the NOEL for the F1 and F2 offspring was 125 ppm. In developmental toxicity studies in rats, rabbits, and hamsters styrene was not a selective toxicant to the fetus and was toxic at only those doses that produced matarnal tovicity In humans, styrene is associated with central nervous system depression (headache, fatigue, nausea, and dizziness) at inhalation concentrations greater than 50 ppm. Styrene has also been reported to reduce sensory nerve conductions in occupation settings after exposure to 100 ppm or more. Styrene has also been reported to produce color vision deficiencies (dyschromatopsia) at concentrations greater than 8 ppm (averaging 24 ppm). Twelve epidemiology studies have been reported for styrene and half have supported the hypothesis that styrene produces lymphatic and hematopoetic cancers (LHC). However, those that show an increase of LHC have generally been small in size (limited statistical power), have shown no dose-response relationship, and/or had multiple chemical exposures. Of the six studies that have not shown an association with styrene and LHC, these studies tended to be larger in size (higher statistical power), had an older study population, and had good exposure data. Overall, the weight of evidence suggests that there is not an association of LHC and styrene exposure in humans. In a recent inhalation cancer bioassay, Sprague Dawley derived rats (70/sex/group) were exposed whole body to styrene vapor at 0, 50, 200, 500, or 1000 ppm 6 h/day 5 days / week for 104 weeks. Males exposed to 500 and 1000 ppm and females exposed to 200 ppm and higher gained significantly less weight than the controls. There were no changes of toxicologic significance in hematology, clinical chemistry, urinalysis, or organ weights. Styrene-related non-neoplastic histopathologic changes were confined to the olfactory epithelium of the nasal mucosa. The incidence and severity were related to dose. There was no evidence that styrene exposure caused treatment related increases of any tumor type in males or females or in the number of tumor bearing rats in the exposed groups compared to controls.

In 2-year carcinogenicity bioassays conducted by the National Toxicology Program, rats and mice (50/sex/group) received 0, 500, 1000, or 2000 mg/kg/day and 0, 150, or 300 mg/kg/day, respectively, via oral gavage. In male or female rats and female mice there was no significant difference in tumor incidence when compared to the control groups. In male mice there was a positive association between styrene dose and the incidence of the combination of adenomas and carcinomas of the lung. However, due to the high background incidence of this tumor type in male mice, no firm conclusion was drawn for the carcinogenicity.

In a study that administered styrene (125 and 250 ppm) in the drinking water of rats for 2 years, there was no evidence of carcinogenicity. In other chronic inhalation toxicity studies, rats were exposed to styrene via inhalation at concentrations up to 300 ppm for 4-6 hours/day, 5 days/week, for 1 year or up to 1000 ppm for 2 years. There was a slightly increased, but not statistically significant, incidence of mammary tumors in the females in both studies. Because the control incidence was also high and there was no dose-response relationship the studies were considered to be negative.

Additional Health Hazard Information:	
Acute Toxicity:	Not classified
Reproductive Toxicity:	Not classified; (No data available)
Specific target organ toxicity (single exposure):	Not classified; (No data available)
Specific target organ toxicity (repeated exposure):	Not classified; (No data available)
Listings IARC Group:	Not Listed

SECTION 12: Ecological Information

11(e)

This product is a mixture that has not been evaluated as a whole for health effects. Exposure effects listed below are based on existing health data for the individual components which comprise the barium sulfate particles contained in the mixture.

12(a)	Ecotoxicity	Each barium sulfate powder particle is bound in a polymer matrix mixture and is insoluble in water, thus not expected to be harmful to aquatic organisms.
12(b)	Persistence and degradability	Each barium sulfate powder particle is bound in a polymer matrix mixture and is insoluble in water, thus not expected to be biodegradable.
12(c)	Bioaccumulative potential	Each barium sulfate powder particle is bound in a polymer matrix mixture and is insoluble in water, thus not expected to bioaccumulate.
12(d) 12(e)	Mobility in Soil Other Adverse effects	Insoluble in waterNo data available No data available

SECTION 13: Disposal Considerations

Where possible, recycling is preferred to disposal or incineration. If recycling is not an option, incinerate or dispose of in accordance with federal, state, and local regulations. Collected processing fume condensates and incinerator ash should be tested to determine waste classification. Pigmented, filled, and/or solvent laden product may require special disposal practices in accordance with federal, state, and local regulations. Consult a regulatory specialist to determine appropriate state or local reporting requirements, for assistance in waste characterization and/or hazardous waste disposal, and other requirements listed in pertinent environmental permits. Note: chemical additions to, processing of, or otherwise altering this material may make this waste management information incomplete, inaccurate, or otherwise inappropriate.

Furthermore, state and local waste disposal requirements may be more restrictive or otherwise different from federal laws AEC-SDS Ecomass Compound 0700BI Series V.4 02-28-2019.xlsx Page 8 of 11 This product contains one or more substances that are listed with the state of California as a hazardous waste:

Chemical Name	California Hazardous Waste Status	
Barium Sulfate 7727-43-7	Toxic soluble	

SECTION 14: Transport Information

In accordance with DOT, this product is not regulated for transport.

14(a)	UN Number:	None
14(b)	UN Number Shipping Name:	None
14(c)	Transport Hazard Class(es):	None
14(d)	Packing Group:	None
14(e)	Environmental Hazards:	Not a marine pollutant
14(f)	Transport in Bulk:	None
14(g)	Special Precautions:	None

SECTION 15: Regulatory Information

US Federal Regulations

SARA - Section 302 Extremely Hazardous Chemicals:

The components in this product are either not SARA Section 302 regulated or regulated but present in negligible concentrations.

None

SARA - Section 311/312 Hazard Classes: Barium Sulfate Acute health hazard

SARA - Section 313 - Toxic Chemicals:

Unless specifically identified in this section, this material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.

Name	lame Product Identifier		SARA 313 - Threshold Values %
Barium Sulfate	7727-43-7	< 100	1.0

CERCLA - Comprehensive Environmental Response, Compensation, & Liability Act - Reportable Quantity (RQ) Unless specifically identified in this section, the components in this product are either not CERCLA regulated, regulated but

present in negligible concentrations, or regulated with no assigned reportable quantity.

Name	Hazardous Substances RQs	CERCLA EHS RQs
None		

Clean Water Act				
Component	CWA -	CWA - Reportable	CWA - Toxic	CWA - Priority Pollutants
None				

Clean Air Act - Not applicable

OSHA	Unless specifically identified in this section, the components in this product are not considered hazardous by OSHA:
	None

Chemical Inventory Status

European Inventory of Existing Commercial Chemical	EU, EINECS	Listed
United States TSCA (Toxic Substances Control Act) Inventory	TSCA	Listed
Canadian Domestic Substances List	DSL	Listed
China. Inventory of Existing Chemical Substances Produced or Imported in China	IECSC (CN)	Listed
Japan. ENCS - Existing & New Chemical Substances Inventory	ENCS (JP)	Listed
Japan. ISHL - Inventory of Chemical Substances	ISHL (JP)	Listed
Korea. Korean Existing Chemicals Inventory	KECI (KR)	Listed
Philippines Inventory of Chemicals and Chemical Substances	PICCS (PH)	Listed
Australian Inventory of Chemical Substances	AICS	Listed

US State Regulations

California Prop. 65: Components in this product known to the State of California to cause cancer, birth defects, or any other reproductive defects are listed below:

Chemical Name	Weight %	California Proposition 65:
Acrylonitrile 107-13-1	<100 ppm	Type of Toxicity: cancer
Ethylbenzene 100-41-4	<100 ppm	Type of Toxicity: cancer

SECTION 16: Other Information

Revision Date: February 28, 2019

Version Number: 04

Ecomass[®] is a registered trademark.

ABBREVIATIONS / ACRONYMS / REFERENCES:

- AND EU Agreement for the International Transport of Dangerous Goods by Inland Waterways, as amended
- ADR EU Agreement for the International Carriage of Dangerous Goods by Road, as amended
- CAS Chemical Abstracts Services (Division of the American Chemical Society)
- GHS Globally Harmonized System of Classification and Labelling of Chemicals, as amended
- HMIS Hazardous Materials Identification System
- IATA International Air Transport Association
- ICAO International Civil Aviation Organization
- IMDG International Maritime Code for Dangerous Goods, as amended
- LCSO Lethal Concentration of 50 Percent of Organisms
- MARPOL International Convention for the Prevention of Pollutants from Ships, 1973, as amended
- MHLW Japanese Ministry of Health, Labor, and Welfare

NFPA 704 National Fire Protection Association

- OE Oil Extended
- OEL Occupational Exposure Limit
- RID EU Standards Regulations Concerning the International Transport of Dangerous Goods by Rail
- TLV Threshold Limit Value
- TWA Time Weighted Average
- UN United Nation
- USP United States Pharmacopeia for the Testing of Biological Endpoints for Medical Devices

DISCLAIMER:

The information is based on present knowledge. This does not constitute a guarantee for any product features or specifications. It does not establish a legal contractual relationship. The information, data, and recommendations are made to our reasonable ability in good faith and obtained from reliable sources. Completeness is not guaranteed. It is intended to describe the products for the purpose of Health, Safety, and Environmental requirements only. The Safety Data Sheet is guidance for product uses. Advice applies to the products as originally supplied. Where other ingredients are added in the processing of these products, it is the users responsibility to evaluate or consult on their safe handling and use. It is the responsibility of the user to comply with all Local, Federal, and International Legislation and Local Permits when using. Further, since the conditions and methods of use are beyond the control of Americhem Engineered Compounds, Americhem Engineered Compounds expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information.

We believe the information set forth in this document to be true and accurate, but any recommendations, statements, or suggestions made in the foregoing text are without any warranty or guarantee whatsoever, and shall establish no legal duty or responsibility on the part of the author(s) or their employer. Furthermore, nothing set forth above shall be construed as a recommendation to use any product in conflict with any existing patent rights.

Americhem Engineered Compounds for itself and the said author(s), expressly disclaims any and all liability for any damages or injuries arising out of any activities relating in any way to this publication. NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY, OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE INFORMATION PROVIDED HEREIN.

This information is based on our current knowledge and is intended to describe the product for the purposes of health, safety, and environmental requirements only. It should not therefore be construed as guaranteeing any specific property of the product.