



# Technical Data Sheet

4101 Parkstone Heights Drive, Suite 380  
Austin, Texas 78746-7482  
512-306-0020

**Material:** Ecomass® Compound 1050TU96

*Nontoxic alternative to Lead (Pb), weighting, balancing and radiation shielding applications*

**Description / Features:** High Specific Gravity, Tungsten Powder Filled Polyamide (PA) Alloy, Good Toughness

**Processing Method:** Injection Molding

## Physical Properties

	Test Method	Value	Units
<b>Physical Properties</b>			
Product Form		Pellets	
Specific Gravity	ASTM D792	11.00	
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D638	5,000	psi
Tensile Modulus	ASTM D638	935,000	psi
Tensile Elongation at Break	ASTM D638	1.75	%
Flexural Modulus	ASTM D790	720,000	psi
Flexural Strength	ASTM D790	7,050	psi
Izod Impact Strength, notched	ASTM D256	2.1	ft-lb/in
<b>Thermal Properties</b>			
Heat Deflection Temperature at 66 psi	ASTM D648	275	°F
Heat Deflection Temperature at 264 psi	ASTM D648	250	°F
<b>Electrical Properties</b>			
Surface Resistivity	ASTM D257	0.21	ohms/sq
<b>Processing Information</b>			
Melt Temperature Range		400 - 490	°F
Mold Temperature Range		135 - 180	°F
Mold Shrinkage Rate	ASTM D955	0.005 - 0.006	in/in
Pre-Drying Conditions		4 hrs @ 165°F	

The information provided above is based on laboratory testing using test methods indicated and is believed to represent nominal results of those tests. Because conditions under which this material may be processed, tested or used cannot be anticipated, no warranty is given, either expressed or implied, as to the accuracy or reproducibility of this information or for the fitness of this material for any particular use. This material is sold with the express understanding that purchasers, processors or other users of this material have sole responsibility, through performance of their own testing, to determine the suitability of this material for any particular use.

Ecomass® Compounds are manufactured by Americhem® under license from Ecomass Technologies.

Ecomass® is a registered trademark